





Leaf

This flatwoven article is in the Textaafoam Comfort collection. Softness, volume and elegance are characteristic for this collection.

A luxury chenille bouclé yarn has been woven in the weft-direction. This gives this chunky and trendy new article a great hand feel. With no less than 770 grams per running meter, it is a very heavy fabric which contributes to the durability.

Leaf is a piece dyed article with a light melange aspect. Our product development team launches Leaf directly in a wide colour line. A combination of commercial and trendy colours and perfect to combine with our velvets Adore, Royal, Juke and Seven.

Leaf is washable at 30 degrees. Available from stock now.

* Please wash the cover inside out. We also recommend to put the fabric back on the furniture slightly damp after washing to ensure it dries evenly.


***Textaafoam** originals Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition


/ Faceside 100%PES
/ Chenille flatweave

Suitable for


Sofa's, beds, chairs with fitted
and loose fitting upholstery




ivory 101




ashgrey 40



stone 181



steel 149



taupe 12



brown 15




grey 65




lava 165




espresso 123




niagara 158



indigo 90



darkblue 48




eucalyptus 193




forest 162




mustard 06



scarlet 141



winered 39



hazel 96

Leaf - Article passport




A luxury chenille bouclé yarn has been woven in the weft-direction. This gives this chunky and trendy new article a great hand feel.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Statistic Code	54075200	
Coating	SBR	
Dyeing method	yarn dyed	
Available colours	18	

Durability specifications

Test		Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
					DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage		DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 8.000	min. 16.000	C
Pilling		DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light		DIN EN ISO 105-B02:2014-11, Process 3, exposure level 5							
		light colours	CTL	grade	5		min. 4	min. 5	B
		middle colours	CTL	grade	5		min. 4	min. 5	B
		dark colours	CTL	grade	5		min. 4	min. 5	B
Colour fastness to rubbing		DIN EN ISO 105-X12:2016-11							
		light colours	CTL	grade	5	5	dry: 4, wet: 3	Dry: min. 4, wet: 3-4	A/A
		middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	Dry: min. 4, wet: 3-4	A/A
		dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	Dry: min. 4, wet: 3-4	A/A
Ignatability		BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324, Schedule 4 part I, Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 30							
Material weight in grams per linear meter	± 770							
Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	2.666	781	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	255,3	223,5	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	4,5	3,5	max. 5	max. 4	B/A
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	± 0,0	± 0,0	n/a	n/a	A/A



We recommend to immediately place the cover back to the piece of furniture slightly damp after washing.



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl